

PROPERTY	UNIT	GUARANTEE	LIMIT	TEST METHOD
Penetration at 25°C	0.1 mm	Class 3	25-55	EN 1426
Softening Point	°C	Class 6	≥60	EN 1427
Cohesion				
Force ductility (50 mm/min traction)	J/cm ²	Class 7	≥ 3 at 10°C	EN 13589
Elastic recovery at 25°C	%	Class 1	TBR	EN 13398
Resistance to hardening:				
Retained penetration	%	Class 7	≥60	EN 12607-1
Increase in softening point	°C	Class 2	≤ 8	
Decrease in softening point ^a	°C	Class 1	TBR	
Change of mass ^b	%	Class 2	≤ 0.3	
Flash Point	°C	Class 2	≥ 250	EN ISO 2592

^a Softening point after EN 12607-1 (RTFOT) may increase or decrease. If there is a decrease in softening point, the result will be reported.

^b Change of mass can be positive or negative.