

PROPERTY	UNIT	GUARANTEE	LIMIT	TEST METHOD	
				ASTM	IP
Density (at 15 °C)	Kg/m3	948,0-1013,7		D 1298 D 4052	
Color, (10 % Dilute)	ASTM	8,0	Max	D 1500	
Flash Point	°C	200	Min	D 92	
Pour Point	°C	40	Max	D 97 D 5950	
Sulfur	wt %	report			336
Viscosity (at 100 °C)	cSt	16,0-44,0		D 445	
Aniline Point	°C	70	Max	D 611	
Water	wt %	0,1	Max	D 95	

This product is produced only in İzmir Refinery.